



TEST REPORT

Client: Steven Hargreaves Textile Group Ltd
 Overbrook House
 14 Brookes Lane
 Whalley
 Lancashire
 BB7 9RG

Entry No: 72595

Date received: 13/11/2015

Client's Description: Sample of fabric: Stamford Black / White Mattress Ticking, Twill Weave, 100% Cotton

Test Required: Flammability BS 7175 ignition sources 0, 1 (on top only) & 5 (on top & below)

Pre-treatment: None

Conditioning: A minimum of 72 hours at indoor ambient and then 24 hours at 65+/-5% Relative Humidity, 20+/-5° C

Date Tests Completed: 18/11/2015

Method of Test: BS 7175: 1989 (2008) Section 3

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the bedcovers in use.

Ignition Source	Positions	Observations	Result
0 (cigarette)	On top	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	On top	Flaming ceased within the specified two minute period after removal of the butane and no progressive smouldering occurred	PASS
5 (wood crib)	(i) On top (ii) Below Overhang	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Dale Brockbank
 Materials Testing Manager
 19 November 2015

❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 ❖ Uncertainty budgets for test methods contained within this report are available on request.
 This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

